

# TECHNICAL DATA SHEET ULTRAMARINE BLUE UPL 1100

#### **GENERAL INFORMATION:**

1. IDENTITY : Sodium Aluminium Sulpho Silicate

2. CAS NUMBER : 57455-37-5 / 101357-30-6

3. COLOUR INDEX NUMBER : Pigment Blue 29 | C.I.No. 77007

#### **COLOUR PROPERTIES:**

(Blue reduced with five times its weight of Rutile Titanium Dioxide, drawn down and compared with its Batch Standard in CIE Lab Scale)

1. TINTING STRENGTH (%) :  $100 \pm 5$ 

2. COLOUR DIFFERENCE DE\* : 1.0 Unit Maximum

 $DL^*$  :  $\pm 0.5$  Unit  $DA^*$  :  $\pm 0.5$  Unit  $DB^*$  :  $\pm 0.5$  Unit

#### **OTHER PHYSICAL AND CHEMICAL PROPERTIES:**

1. APPEARANCE
2. APPARENT DENSITY (g/cc)
3. MOISTURE CONTENT AT 105°C (% BY WT.)
4. WATER SOLUBLE MATTER (% BY WT.)
5. FREE SULPHUR
5. Blue Powder
5. 0.45 to 0.60
5. 1.0 % Maximum
6. 2.0% Maximum
7. 100 ppm Maximum
7. 100 ppm Maximum

6. OIL ABSORPTION (% BY WT.) : 34 to 37

7. MEDIAN PARTICLE DIAMETER : 2.0 Microns maximum

8. RESIDUE ON 45 MICRONS SIEVE (% BY WT.): 0.2 Maximum

#### **COLOUR FASTNESS PROPERTIES:**

1. HEAT STABILITY : 350°C for 5 Minutes

2. LIGHT (DAY LIGHT AND XENON LAMP)

IN MASS TONE : 7/8 on Wool scale IN REDUCED TONE : 7/8 on Wool scale 3. WEATHER FASTNESS : 4/5 on Grey scale

4. IN ACIDS : Poor 5. IN ALKALIS : Good

### **TOXICITY:**

Least toxic and a safe pigment for industrial applications. It is ecologically non-hazardous and does not create any skin irritation.

## **USAGE IN COSMETICS:**

Conforms to various regulations in most of the countries in the world

#### Note:

The information provided above is for general guidelines only and subject to change without notice. Ultramarine & Pigments Limited assumes no responsibility and users are advised to test the products for suitability prior to use on a commercial or production scale.